

Battery Specification

Nominal Voltage	12V
Number of cell	6
Design Life	10 years
Nominal Capacity 77°F(25°C)	
10 hour rate (12.00A, 10.5V)	120.0Ah
5 hour rate (19.2A, 10.5V)	96.00Ah
1 hour rate (73.3A, 9.6V)	73.30Ah

Internal Resistance

Fully Charged battery 77°F(25°C) ≤5.3mOhms

Self-Discharge

3% of capacity declined per month at 20°C(average)

Operating Temperature Range

Discharge -20~60°C

Charge -10~60°C

Storage -20~60°C

Max. Discharge Current 77°F(25°C) 950(5s)

Short Circuit Current 2250A

Charge Methods: Constant Voltage Charge 77°F(25°C)

Cycle use 2.40-2.45VPC

Maximum charging current 36.0A

Temperature compensation -30mV/°C


Standby use 13.6-13.8V

Temperature compensation -20mV/°C

Dimensions and Weight

Length(mm / inch)	410/16.14
Width(mm / inch)	176 / 6.93
Height(mm / inch)	227 / 8.94
Total Height(mm / inch)	227 / 8.94
Approx. Weight(Kg / lbs)	34.0 / 74.9

* Weight deviation: ± 3%



Battery Construction

Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper/Plug	Fiberglass	Sulfuric acid

Discharge Constant Current (Amperes at 77°F25°C)

End Point									
Volts/Cell	10min	15min	30min	1h	3h	5h	10h	20h	
1.60V	258	209	117	73.3	29.9	20.3	12.4	6.43	
1.65V	244	201	114	72.8	29.3	20.1	12.3	6.41	
1.70V	231	193	110	71.3	28.7	19.7	12.2	6.38	
1.75V	217	184	106	69.1	28.0	19.2	12.1	6.35	
1.80V	203	177	104	67.0	27.2	18.9	12.0	6.30	

Discharge Constant Power (Watts at 77°F25°C)


End Point									
Volts/Cell	10min	15min	30min	45min	1h	2h	3h	5h	
1.60V	460	367	225	159	147	82	58.0	40.7	
1.65V	437	354	218	156	145	80	57.3	40.5	
1.70V	414	343	211	153	143	79	56.6	40.2	
1.75V	392	331	204	149	139	77	56.0	40.0	
1.80V	367	319	198	146	134	75	55.0	39.6	

(Note)The above characteristics data are average values obtained within threecharge/discharge cycles. All data shall be changed without notice, Neata reserves the right to explain and update the information.


General Features

- Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.
- Case and cover available in both standard and flame retardant ABS.


Discharge Characteristics Curve




Charge Characteristic Curve For Standby Use




Cycle Life In Relation To Depth Of Discharge




Temperature Effects On Capacity




Relationship Between Charging Voltage And Temperature



Storage Characteristics



Effect Of Temperature On Long Term Life



Life Characteristics Of Standby Use

